

MEXMID B GF30H NC

| | | | |
|--------------------|---|--------------------------------|------------------------|
| Description | Polyamide 6 medium viscosity with 30% glass fiber reinforced, heat stabilized | | |
| Color | Natural Color | Additional formulations | |
| Processing | Injection | HR - Resistance to hydrolysis | EL - High impact |
| Norm | - | Viscosity from 2.4 to 3.3 | IB - Hybrid Mineral+GF |
| Norm | - | UL94 - Flame | UV - Light stabilized |

Applications: Piezas exteriores, rejillas de radiador, manijas de puertas y componentes de motor parts. Piezas mecánicas de alta resistencia, componentes de carga y piezas de maquinaria.

| Mechanical Properties | Values | Unit | ISO |
|--|---------------|-------------------|------------|
| Density | 1,36 | g/cm ³ | 1183 |
| Filler Content | 30 | % | 3451 |
| Relative viscosity (1% in 96% H ₂ SO ₄) | 2.7 ± 0.10 | - | 307 |
| Melting Point (DSC) | 222 | ° C | 3146 |

| Mechanical Properties | Dry/Wet | Unit | ISO |
|---------------------------------------|----------------|-------------------|------------|
| Tensile elongation at break | 3/8 | MPa | 527-2 |
| Tensile strength at break | 180/110 | MPa | 178 |
| Flexural Modulus | 8500/5000 | MPa | 178 |
| IZOD Impact strength, notched (23° C) | 9/15 | KJ/m ² | 180 1eA |

| Thermal Properties | Values | Unit | ISO |
|---------------------------|---------------|-------------|------------|
| HDT method A (1.820 MPa) | 210 | ° C | 75-1 |

| Flammability | Values | Unit | ISO |
|------------------------|---------------|-------------|------------|
| Flame rating at 3.2 mm | HB | | UL94 |

| Processing Conditions | Values | | | |
|------------------------------|---------------|-----------------------|----------|------|
| Drying | 4-6h/90° C | Suggeste max moisture | 0.15 | % |
| Hopper | 260 ÷ 270° C | Min temperture | 270 | ° C |
| Front | 260 ÷ 270° C | Max temperture | 320 | ° C |
| Middle | 260 ÷ 270° C | Injection rate | High | |
| Rear | 260 ÷ 270° C | Injection pressure | 40 ÷ 120 | MPa |
| Nozzle | 265 ÷ 270° C | Injection time | 3 ÷ 15 | Sec. |
| Hot Runner Temp, | 270 ÷ 280° C | Screw Back | 3,5 | Bar |
| Moulds | 80 - 120° C | Cooling time | 30 ÷ 90 | Sec. |

Due to the high moisture absorption of PA6, special attention should be given to drying before processing. If the humidity exceeds 0.2%, it is recommended to dry in hot air at temperatures above 80° C for 8 hours. If the material has been exposed to the air for more than 8 hours, vacuum drying at 105° C for at least 8 hours is advised.

Melting Temperature: 260-280° C. For reinforced varieties, the melting temperature is 270-290° C.

Mold temperature significantly affects crystallinity, which, in turn, impacts the mechanical properties of the plastic parts. It is recommended to set the mold temperature at 80~90° C. For thin-walled, longer-flow plastic parts, such as the nylon cable tie production, a higher mold temperature is also recommended. Increasing the mold temperature can enhance the strength and rigidity of the plastic parts but reduces toughness.

Injection Pressure: Generally between 750-1250 bar (depending on the material and product design).

Injection Speed: High-speed (slightly reduced for reinforced materials).

Due to the short solidification time of PA6, the gate's position is crucial. The gate aperture should not be smaller than 0.5*t (where t is the thickness of the plastic part). If using a hot runner, the gate size should be slightly smaller than with a conventional runner, as the hot runner helps prevent premature solidification of the material. If using a submerged gate, the minimum diameter of the gate should be 0.75mm.

The information and data contained herein is believed to be accurate and are given in good faith. However, accuracy is not guaranteed and no warranty nor representation in such regard or in connection with any of the products referred to herein is given and PMexpolimeros disclaims all liability accordingly, whether in contract tort or otherwise.